ELI-CAST FR/453 ELECTRICAL INSULATING RESIN

PRODUCT: Eli-Cast FR/453 is filler extended two part Polyurethane Resin

COLOUR: Resin: Electro Brown

Hardener: Brownish clear

Mixed: Electro Brown

VISCOSITY / 25°C: Resin: 5 000 – 5 500 mPa.s Hardener: 200 – 200 mPa.s Mixed: 2 000 – 2 500 mPa.s

1111/04. 2 000 2 000 1111

APPLICATION: By casting

MIXING RATIO: <u>By Weight</u> <u>By Volume</u>

100 parts of Resin 100 parts of Resin 25 – 26 parts of Hardener 34 – 35 parts of Hardener

SPECIFIC GRAVITY: Resin: 1.65 g/cm³
Hardener: 1.20 g/cm³

POTLIFE / 25°C: 30 Minutes

GELTIME / 25°C: 35 – 40 Minutes

SETTING TIME / 25°C: $1 - 1^{1/4}$ Hours

EXOTHERM: Maximum 60°C (500ml volume)

ADHESION: To PVC, Aluminium, Lead, Copper: Very good

To Cleaned, Flamed Polyethylene: Good

FLASHPOINT: > 200°C

HEAT RESISTANCE: Maximum 80°C

HARDNESS: (Cured 24h / 25°C) Shore D: 80 – 85

011070 21 00 00

DIELECTRIC STRENGTH: 21 kV/mm (Method 210C)

VOLUME RESISTIVITY: 10 x 10¹² Ohm/cm

RESISTANCE: To Water, Oil, diluted Acids, Alkaline: Very good

Solvents: Aromatic / Aliphatic Hydrocarbons: Good

Esters, Ketons, Chlorinated Hydrocarbons: Not resistant

(Individual tests are recommended)

2/....

Page 2 FR/453

HYDROLYTIC STABILITY:

Excellent

WATER ABSORPTION:

(After 24 hour immersion in distilled water):

0.3 %

STORAGE STABILITY:

12 Months stored under dry and cool conditions in sealed packaging

TOXICITY:

Very low toxicity at ambient temperatures. However, gloves must be worn

and adequate ventilation must be ensured during application.

NOTICE

The technical specification and/or our technical advice whether verbal, in writing or by trials is given in good faith and based on our test results obtained but without warranty. It does not release the user from the obligation to test the products supplied by us or any third party as to the

suitability for the intended application.

The application, use and processing of the products are beyond our control and Elite Chemical Industries legal obligation in respect of any sale of its products shall be determined by the terms of its conditions of sale.

JANUARY 2011